

Quality Test Report

Natural Dyed Fabric



Fabric Info

Fabric Code	GWTX0024	Composition	Tencel 100%
Dyestuff	Gallnut		

Fastness Quality

Fastness		Perspiration	
Light	Washing	Acidic	Alkaline
4	4	3~4	3~4

Quality Test Reported by : **KOTERI**

- **Washing** - KS K ISO 105 C06 : 2010, A1S, 30 minutes mechanical wash at (40 ± 2) °C, In 0.4% ECE Reference Detergent Solution with 10 steel balls
- **Light** : Xenon Arc Fading Lamp Test, KS K ISO 105 B02 : 2014, Method 3 Modified, Exposure Cycle A1
- **Complex** : Xenon Arc / KS K 0701 / 20 Hours
- **Rubbing** : KS K ISO 105 X12 : 2016